Serge Ferrari
industries







Protect



Mesh 330-332


Précontraint®

Protect Mesh 330 - 332

	**Light ivory** **RAL 1015**	**330-1076*** **332-1076**		**White** **RAL 9016**	**330-1066*** **332-8100**
	**Green** **RAL 6005**	**330-50201*** **332-50201**		**Dark Grey** **RAL 7037**	**330-1070*** **332-1070**
	**Black** **RAL 9005**	**330-1075*** **332-1075**		**Caribbean** **RAL 5015**	**330-1053*** **332-1053***

* Colors subject to MOQ & specific lead time

Protect Mesh 330PL



Fluorescent orange **330-50211***
Width 180 cm

* Colors subject to MOQ & specific lead time

Protect
Mesh 330 - 332

The most closed & lightest mesh of the range suitable for various applications

Main advantages

- Excellent efficiency in reducing wind flow
- Light and resistant
- Hight dimensionnal stability thanks to Précontraint® technology

Main applications

- Protection net - Dust protection - Windbreak
- Pool cover - Air/insects filtration
- Scaffolding cover - Masquing equipment
- Ski resort security signage only for 330PL

	Protect Mesh		
	330PL	**330**	**332**
	Technical specification		
Support cloth DIN 60001	1,100 dtex PES HT		
Coating	PVC		
Finish	Acrylic varnish		
Weight EN ISO 2286-2	340 g/m² • 10.0 oz/sq. yd		
Width	180 cm • 70.9 in	267 cm • 105.1 in	267 cm • 105.1 in
Standard format length	±50 lm/±300 lm • ±54.68 yd/±328.08 yd		
	Physical properties		
Tensile strength (warp/weft) EN ISO 1421	230/160 daN/5 cm • 517/360 lbs/2 in		
Tear strength (warp/weft) DIN 53.363	30/15 daN • 67/34 lbs		
Openess factor	14%		
Permeability to air* NF EN ISO 9237	2.192 l/dm²/min		
Temperature resistance DIN EN 1876-1	-30°C/+70°C • -22°F/+158°F		
	Fire resistance		
Rating - International fire certificate available, such as**	–		**B1/**DIN 4102-1 **M2/**NF P 92-507
	Environmental properties		
Carbon impact EN 15804 + A1***	–		2.46 Kg CO_2 eq/m²
	Managment systems		
	Quality: ISO 9001 • **Environment**: ISO 14001 • **Energy**: ISO 50001		
	Certifications, labels		

Précontraint® Technology

* Test surface 20 cm², pressure 200 Pa
** Contact us for latest certificate updates & validities
*** External 3d party verification

[1] Summarizes the group's CSR project focused on human, to align economic performance and positive impact.

Quoted technical characteristics are average values subject to +/-10% tolerance.

The buyer of our products is fully responsible for their application and their transformation with regard to any possible third party. The buyer of our products is responsible for their implementation and installation according to the standards, wormanship and safety regulations in force in destination countries. For information on our contractual warranty, please refer to the relevant terms and conditions. The values quoted above represent results of tests performed in compliance with common design practices and are provided for information only to enable customers to make the best use of our products. Our products are subject to changes based on technical advances and we reserve the right to modify their characteristics at any time. The buyer of our products is responsible for checking the validity of the above data.

The colours and textures represented are provided as reference only.

Précontraint is a Serge Ferrari SAS registered trademark.
Ref CT-02565 • 07/2026 • PDF ONLY

EN

Photo credits: ©SergeFerrari

Serge Ferrari group

sergeferrarigroup.com