
Serge Ferrari
architecture

Flexlight

402 HT

Highly Translucent



Flexlight 402 HT

Highly translucent membrane

Main advantages

- Highly translucent: very high light transmission (48% according NFP 38.511)
- Easy to weld
- Exceptional dimensional stability due to Précontraint® technology

Main applications

- Static and permanent structures
- Inflatable structures




Flexlight 402 HT

Highly translucent

Serge Ferrari
architecture




Ultra white **402-1399**



White **402-8145**

Exclusive Précontraint® technology

This unique, world-patented technology involves maintaining the composite in bi-axial tension throughout the manufacturing cycle. It ensures our materials' exceptional performance characteristics, which ensure they exceed market standards in terms of long-term stability, strength, coating thickness and flatness.



1	**High-tenacity polyester micro-yarn reinforcing mesh**	Higher resistance to elongation and tearing
2	**Coating under bi-axial, warp and weft tension**	No deformation during installation and usage
3	**Coating thickness covering top of yarns and dirt repellent surface treatment**	Enhanced aesthetic and structural durability
4	**Extremely flat and thin**	Easy-to-clean smooth surface ensuring compactness and easy rolling

Flexlight 402 HT

	Technical properties
Yarn type	PES High tenacity
Yarn treatment	Standard wicking treatment
Coating	Antifungal-treated high-performance PVC
Finish	Lacquer both sides
Weight EN ISO 2286-2	520 g/m² • 15.3 oz/yd. sq
Width	267 cm • 105.1 in
Length of rolls	Rolls: 50 lm • 54.68 yd Jumbo rolls: 300 lm • 328.08 yd
	Physical properties
Tensile strength (warp/weft) EN ISO 1421	230/220 daN/5 cm • 517/495 lbs/2 in
Tear strength (warp/weft) DIN 53.363	20/20 daN • 45/45 lbs
Elongation under load (warp/weft)	<1% / <1%
Adhesion EN ISO 2411	8/8 daN/5 cm • 18/18 lbs/2 in
Extreme working temperatures	-30°C/+70°C • -22°F/+158°F - In static position internal test
	Fire resistance
Rating - International fire certificate available, such as*	**B-s2,d0**/EN 13501-1
	Environmental properties
Carbon impact EN 15804 + A2	1.75 kg CO_2 eq./m²
	Management system
	Quality: ISO 9001 • **Environment**: ISO 14001 • **Energy**: ISO 50001
	Certifications, labels, warranty

Précontraint® Technology

10-year warranty
For internal use only

* Contact us for latest certificate updates & validities
[1] Summarizes the group's CSR project focused on human, to align economic performance and positive impact.

Quoted technical characteristics are average values subject to +/-5% tolerance.

The purchaser of our products is responsible for their application or transformation in relation to possible third party rights. The purchaser of our products is responsible for their installation in compliance with the standards, working practices and safety regulations of their destination country. Please refer to our warranty document with regard to contractual liability.
Values quoted in this document are commonly used test results for design purposes. They are given for information only in order to offer our customers optimum usage of our products. Our products are subject to improvements resulting from technical developments and we reserve the right to modify their characteristics at any time. The purchaser of our products is responsible for checking the above data.

The colors and textures presented are included for information only.

Flexlight and Précontraint are Serge Ferrari sas registered trademarks.
Ref. 1779-GB • 08/2026 • PDF ONLY

EN

Photo credits: ©Ben Rahn/A-Frame, ©FredTgelaar - Polyned

Serge Ferrari group

sergeferrarigroup.com