Soltis 96

	Color	Proof
Technical properties		
Openness factor	4%	0%
Weight EN ISO 2286-2	400 g/m² • 11.8 oz/sq. yd	620 g/m² • 18.3 oz/sq. yd
Thickness	0.45 mm • 450 microns	0.56 mm • 560 microns
Width	120 cm - 267 cm • 47.2 in - 105.1 in	267 cm • 105.1 in
Roll length		
In 120 cm • 42.7 in Width	40 lm • 43.74 yd	–
In 267 cm • 105.1 in Width	40 lm • 43.74 yd	35 lm • 38.28 yd
Physical properties		
Tensile strength (warp/weft) EN ISO 1421	220/220 daN/5 cm • 495/495 lbs/2 in	220/220 daN/5 cm • 495/495 lbs/2 in
Tear strength (warp/weft) DIN 53.363	30/25 daN • 67/56 lbs	25/20 daN • 56/45 lbs
Sealing EN ISO 811	–	10,000 mm • 393.7 in
Environmental properties		
Carbon impact EN 15804 + A1	2.38 kg CO_2 eq/m²	3.08 kg CO_2 eq/m²
Fire resistance		
Rating	**M2**/NF P 92-507 **B1**/DIN 4102-1 **M2**/UNE 23727 NFPA 701 Method 1 CAN/ULC S109 AS/NZS 1530.2 & 1530.3	**M2**/NF P 92-507 **B1**/DIN 4102-1 **M2**/UNE 23727 **Class 1**/EN 13773 **Class 2**/UNI 9177 BS 5867-2 Type B **Schwerbrennbar-Q1-Tr1**/ONORM A 3800-1 NFPA 701 Method 1 & 2 CSFM T19 **Class A**/ASTM E84 CAN/ULC S109 AS/NZS 1530.2 & 1530.3
Euroclass EN 13501-1	**B-s2,d0**	**B-s2,d0**
Management system		
	Quality: ISO 9001 • **Environment**: ISO 14001 • **Energy**: ISO 50001	

Certifications, labels, warranty

Précontraint® Technology | 5-year warranty

Tools and Services

Soltissim: tool to evaluate energy savings that can be achieved with Soltis solar protection. Contact your Serge Ferrari representative.

[1] Summarizes the group's CSR project focused on human, to align economic performance and positive impact.

The technical data above are averaged values with a +/-5% tolerance.
The global warming value has been validated by the Bureau Veritas certification company.
The purchaser of our products is responsible for their application or transformation in relation to possible third party rights. The purchaser of our products is responsible for their installation in compliance with the standards, working practices and safety regulations of their destination country. Please refer to our warranty document with regard to contractual liability.
Values quoted in this document are commonly used test results for design purposes. They are given for information only in order to offer our customers optimum usage of our products. Our products are subject to improvements resulting from technical developments and we reserve the right to modify their characteristics at any time. The purchaser of our products is responsible for checking the above data.
The colors and textures presented are included for information only.

Serge Ferrari group

sergeferrarigroup.com

Soltis and Précontraint are Serge Ferrari SAS registered trademarks.
Ref. SC96EN • 05/2026

EN

Photo credits: ©Pierre Le Chatelier, ©Frank Fleury, ©Yann Geoffray, ©Serge Demailly